

INTERNATIONAL  
STANDARD

ISO  
24497-1

First edition  
2007-11-01

---

---

---

## Non-destructive testing — Metal magnetic memory —

### Part 1: Vocabulary

*Essais non destructifs — Mémoire magnétique des métaux —  
Partie 1: Vocabulaire*



Reference number  
ISO 24497-1:2007(E)

© ISO 2007

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 24497-1 was prepared by the International Institute of Welding, Commission V, *Quality control and quality assurance of welded products*, recognized as an international standardizing body in the field of welding in accordance with Council Resolution 42/1999.

Requests for official interpretations of any aspect of this part of ISO 24497 should be directed to the ISO Central Secretariat, who will forward them to the IIW Secretariat for an official response.

ISO 24497 consists of the following parts, under the general title *Non-destructive testing — Metal magnetic memory*:

- *Part 1: Vocabulary*
- *Part 2: General requirements*
- *Part 3: Inspection of welded joints*

## Introduction

The terms established in this part of ISO 24497 are located in a systematic order reflecting the system of concepts in the sphere of non-destructive testing by the method of metal magnetic memory.

One standardized term is assigned to each concept.

The definitions given can be changed, if necessary, by entering derived features into them, revealing the meanings of terms used in them, and indicating the objects relating to the concept defined. The changes should not disturb the concept volume and content defined in this part of ISO 24497.

Standardized terms are printed in boldface font, and their reduced forms are represented by abbreviations (in boldface) or symbols (in lightface).

# Non-destructive testing — Metal magnetic memory —

## Part 1: Vocabulary

### 1 Scope

This part of ISO 24497 specifies terms and definitions for procedures in the sphere of non-destructive testing by the method of metal magnetic memory.

The terms specified in this part of ISO 24497 are mandatory for application in all types of documentation and literature in the sphere of non-destructive testing, using the method of metal magnetic memory included in the scope of standardization works and/or using the results of these works.

### 2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 2.1

##### **metal magnetic memory**

##### **MMM**

after-effect which occurs as residual magnetization in components and welded joints formed in the course of their fabrication and cooled down to ambient temperatures under interaction with weak magnetic fields or due to irreversible change of the local magnetization state of components in zones of stress concentration and damage under working

NOTE Weak magnetic fields are the geomagnetic field of the planet Earth and other external fields in Rayleigh area.

#### 2.2

##### **self-magnetic-leakage field of the components**

##### **SMLF**

magnetic-leakage field occurring on the component's surface in the zones of stable slip bands of dislocations under operational or residual stresses or in the zones of strong heterogeneity in the microstructure of the material

NOTE SMLF characterizes MMM.

#### 2.3

##### **method of metal magnetic memory**

##### **MMM method**

non-destructive testing method based on the analysis of SMLF distribution on components' surfaces for determination of stress concentration zones, imperfections, and heterogeneity in the microstructure of the material and in welded joints

#### 2.4

##### **magneto-dislocation hysteresis**

hysteresis curve due to the pinning of magnetic domain walls (Bloch walls) at dislocation clusters in weak magnetic fields

**2.5**

**critical size of the local zones of instability of the shell ( $l_{cr}$ ) of a component**

minimal distance between the two nearest stable dislocation slip bands in material layers occurring at the moment of loss of shell stability of the component under the influence of loads

**NOTE** This critical size is characterized by the distance between the two nearest SMLF extreme values normalized on the value of the shell dimension.

**2.6**

**SMLF intensity**

characteristic value of the magnetic-leakage field intensity measured on the component surface by the method of metal magnetic memory

**2.7**

**SMLF gradient**

ratio between the difference of the magnetic-leakage field intensity, measured at two adjacent scanning points and the distance between them

**2.8**

**magnetic index ( $m$ ) of the deformation capability of the material**

ratio between the maximum value of the SMLF gradient and the average value

**2.9**

**limiting value ( $m_{lim}$ ) of the magnetic index of the material deformation capability**

limiting value for the ratio between the maximum value of the SMLF gradient, corresponding to the metal tensile strength, and the average value of the SMLF gradient, corresponding to the material yield strength

**2.10**

**SMLF measurement channel**

SMLF intensity measured with a single flux-gate sensor

**2.11**

**base distance between two SMLF measurement channels**

$l_b$   
distance between the two SMLF measurement channels installed at the scanning instrument during the sensor adjustment

**2.12**

**SMLF diagram**

magnetic image of the graph reflecting the SMLF gradient along the scanning path

**2.13**

**discreteness unit of the SMLF intensity recording**

distance between two adjacent scanning points of the magnetic-leakage field intensity measurements

**2.14**

**calibration of the equipment used to measure the metal magnetic memory**

adjustment of the sensors for the measurement of the magnetic-leakage field by using a reference coil and of the position-sensing device by using a length-measurement reference standard

**2.15**

**setting of equipment operational mode by the MMM method**

equipment adjustment according to the instrument main menu and described in the manual

**2.16****interference noise during measurements by the MMM method**

presence of factors distorting the SMLF of the inspection object (IO)

NOTE Factors distorting the SMLF of the inspection object are the following:

- sources of strong and heterogeneous magnetic fields close to the test subject;
- presence of a foreign ferromagnetic product on the test subject and near the region of interest;
- presence of an external magnetic field and/or a welding electric current flow at the test subject;
- presence of a local artificial magnetization.

## Index

### B

**base distance between the two SMLF measurement channels** 2.11

### C

**calibration of the equipment used to measure the metal magnetic memory** 2.14  
**critical size of the local zones of instability of the shell of a component** 2.5

### D

**discreteness unit of the SMLF intensity recording** 2.13

### I

**interference noise during measurements by the MMM method** 2.16

### L

**limiting value of the magnetic index of the material deformation capability** 2.9

### M

**magnetic index of the deformation capability of the material** 2.8  
**magneto-dislocation hysteresis** 2.4  
**metal magnetic memory (MMM)** 2.1  
**method of metal magnetic memory (MMM method)** 2.3

### S

**self-magnetic-leakage field of the components (SMLF)** 2.2  
**setting of equipment operational mode by the MMM method** 2.15  
**SMLF diagram** 2.12  
**SMLF gradient** 2.7  
**SMLF intensity** 2.6  
**SMLF measurement channel** 2.10



---

---

---

---

**ICS 01.040.25; 25.160.40**

Price based on 4 pages